

# FIX-REVOCO

**Pre-mixed mortar for RENDERING and making BOTTOMS in swimming-pools. It is a CONSTANT QUALITY mortar, when the application requires safety, durability and speed.**

## Substrates suitable to take FIX-REVOCO:

- ◆ Rendering or plinths can be produced with FIX-REVOCO on concrete or Gunita with a thickness of up to 25 mm.
- ◆ These substrates must be clean, resistant, solid, free of cracks etc.
- ◆ The ambient temperature must be between +5°C and +35°C.

## Preparing the substrate:

In swimming-pools it will always be essential to first apply a bonding paste.

- ◆ This prior bonding paste is prepared by mixing 1 part PRIMFIX liquid adhesive and 1 part Portland cement.
- ◆ Mix preferably with a an electric mixer.
- ◆ Apply the bonding paste with a brush, roller etc., continuously and uniformly.
- ◆ While the bonding paste is still damp, fill with FIX-REVOCO.



## WARNING

- ◆ FIX-REVOCO must only be mixed with water. Do NOT add sand.
- ◆ Do not use FIX-REVOCO for other than the indicated uses.
- ◆ FIX-REVOCO is not a mortar for laying tiles.



Bonding paste: PRIMFIX + pure Portland.



"Elastic" consistency mortar

## Preparing the FIX-REVOCO mortar:

- ◆ Mix 2.5 l of water with 25 kg of FIX-REVOCO.
- ◆ Mix in a cement-mixer or with a mixer.
- ◆ Mix until the mortar has an elastic consistency and is pleasant to the touch. If necessary, add a little water, but never too much.

### 1st STEP: ESSENTIAL

- ◆ Apply the **bonding paste** with a brush, roller or similar and while it is still damp, take the next step:



Bonding paste: **PRIMFIX** + Portland

### 2nd STEP: Spreading the mortar

- ◆ Apply a first pass of **FIX-REVOCO** with the fine part of the trowel.
- ◆ Once the above fine layer has been spread, it only remains to fill the space between two guides and even it.



First apply a fine layer.

### 3rd STEP: Evening

- ◆ As if it were a normal mortar, even the surface in the traditional manner.



Use the normal tools.



Even between guides.

### 4th STEP (optional): Smoothing

- ◆ If you wish the **FIX-REVOCO** to be as fine as possible, it can easily be smoothed with a fine trowel.



If necessary, it can also be smoothed.

### CONSUMPTION:

Bonding paste (when necessary)	Portland: 0.2 kg./m <sup>2</sup> <b>PRIMFIX</b> : 0.2 l./m <sup>2</sup>
<b>FIX-REVOCO</b>	15-18 kg./m <sup>2</sup> per cm of thickness (always depending on the degree of compacting)



Standard-quality renders.

