

# LATEFIX

## Latex for improving the impermeability and adhesion of FIXCOLOR.

### Preparing the joints:

- ◆ The joints must be clean, with no dust.
- ◆ The ambient temperature must be between +5°C and +35°C.
- ◆ Allow 24 hours between laying the tiles and sealing.
- ◆ In summer, when it is very hot, the joints must be soaked with water before beginning sealing.

### Preparing the mixture:

- ◆ Mix 7.0 l of LATEFIX with 25 kg of FIXCOLOR 0/4, or mix 5.3 l of LATEFIX with 25 kg of FIXCOLOR 4/16.
- ◆ Mix with an electric drill and mixing attachment.
- ◆ Mixing too quickly will provoke the appearance of bubbles on the surface of the joints.
- ◆ Mixing too slowly or by hand will cause the pigment that colours the paste to not be well distributed, and the joint could fade in the future.
- ◆ Mix well and allow the mix to stand for 2 minutes.
- ◆ Re-mix with an electric mixer.
- ◆ The paste is now ready to apply.

### ATTENTION

LATEFIX must not be used:

- ◆ For acid-resistant joints (Use CERPOXI).
- ◆ For dilation joints (Use SELLALASTIC).
- ◆ With temperatures lower than +5°C.



Always mix slowly using an electric agitator.



Use the rubber FIX-SPATULA.

### Applying the mixture:

- ◆ Fill the joints with the FIX-SPATULA.
- ◆ Make diagonal passes on the joints so that the FIX-SPATULA does not collide with the sides of the tile.
- ◆ As you seal, you collect all the excess with the same FIX-SPATULA.

**Cleaning:**

- ◆ After 30 minutes, clean the tiles with the **FIX-SPONGE** or the **FIX-SCOURER** lightly dampened with water.
- ◆ If you use the **FIX-SPONGE**, it must **NOT** be soaked with water, merely dampened.
- ◆ The trowels can be cleaned in the special **FIX-BUCKET**.
- ◆ Only clean once: if you clean more than once, you will only succeed in weakening the colour of the joint.


 Use the **FIX-BUCKET** and the cleaning trowel.

**Final cleaning:**

- ◆ The next day, remove the film of colour with a dry cloth.
- ◆ It is not necessary to use anything else, neither water nor a scourer...only a cloth or dry sponge.


 Use the **FIX-TROWEL FOR CLEANING**.

**Final cleaning in rough tiles:**

- ◆ After 7 days, remove the excess with 1 part **GRESNET** acid and 10 parts water.


 If necessary, use **GRESNET**.

<b>CONSUMPTION:</b>				
Size (mm)	Thickness (mm)	Joint (mm)	Consumption of Fixcolor 4/16 (kg/m <sup>2</sup> )	Consumption of Latefix (kg/m <sup>2</sup> )
100x200	8	4	0.96	0.2
120x240	12	8	2.40	0.5
200x200	8	6	0.96	0.2
250x250	12	10	1.92	0.4
300x300	8	6	0.64	0.14
330x330	15	20	3.64	0.77



Watertight sealing in swimming-pools.